Bona Decking Reviver

Technical data sheet

Bona Decking Reviver is made for cleaning soiled, decayed and/or previously oiled softwood deckings such as larch and pressure impregnated pine deckings. It dissolves old oil and degraded wood, bringing back the light colour the wood used to have when it was new.

- Effective and safe for garden
- Washes away old oil and degraded wood

Technical data

pH-value: Approx. 11

Dilution: For manual use, use as is.

For using with the Bona PowerScrubber, dilute to 1/5 (2 litres of

Decking Reviver and 8 litres of water in the tank).

Shelf life: 3 years from date of production in unopened original container

Storage/transport: The temperature must not fall below +5°C or exceed +25°C

during storage and transport.

Safety: Hazardous – see label for more information

Size(s): 4 litres

Preparations

Remove loose dirt, moss etc from the decking. Check for and correct protruding nails and screws. Protect sensitive surfaces such as plants and aluminium details from stains. Avoid working in direct sunlight.

Manual

- 1. Dampen the decking with water.
- 2. Apply Decking Reviver generously on a 5-10 sqm section and let sit for a few minutes. A good way to apply the product is to first pour the Decking Reviver into a clean, plastic bucket and then distribute it with a roller.
- Scrub section using a hard-bristled brush. Alternatively, a high-pressure washer (equipped with a rotary brush) can be used. Use lowest possible pressure setting.
- 4. Rinse carefully with water and continue with next section (not needed if using a high-pressure washer).
- 5. Allow decking to dry thoroughly before surface treating with decking oil.

Machine processing

Using a Bona PowerScrubber to clean the decking is a more efficient and less labour-intensive method. Very efficient for cleaning grooved decking.

Setup

1. Follow the standard preparation procedure described above and have a water hose handy so that you can flush the decking.





Bona Decking Reviver

Technical data sheet

- 2. To prevent damage to the suction bars on the machine, dismount them or ensure that they are always raised during use.
- 3. Mount orange brushes on the machine. On plainsawn and/or soft wood species, red brushes can be used as a gentler alternative.
- 4. Set the pressure control to medium or high pressure.
- The vacuum unit should not be used while cleaning wooden decks (risk of damage to internal turbine) so ensure it is switched OFF (regulate with foot pedal switch).

Directions for use

- Fill the tank with 8 litres of clean water and top up with 2 litres of Bona Decking Reviver.
- 2. Flush the decking with water.
- 3. Start the machine and use it with the waterpump activated. Scrub a section of the deck along the length of the boards.
- 4. Flush away accumulations of dirt/degraded wood from the cleaned area before it has a chance to dry again.
- 5. Move on to the next section. If the wood has dried, then flush again with water before scrubbing.

Clean the machine thoroughly after use and run it for one minute with only clean water in the tank to rinse internal parts. Allow the decking to dry at least overnight before protecting it with a decking oil such as the Bona Decking Oil. For best results, make a quick pass with an abrasive grit 120 before oiling.

Precautions

- Never expose the machine to rain.
- Always connect the machine to an earthed socket.
- Avoid using several extension cables or ensure that all connectors are watertight.

